

MASTERLITE® PRO FAIRFACED



Masterlite® Pro Fairfaced concrete blocks provide a consistent finish so that walls don't need any exterior finishes.

FEATURES & BENEFITS

- ▶ Low air permeability delivers good thermal performance.
- ▶ Manufactured from carefully selected aggregates to give a close texture and natural colour (one face and one end guaranteed) so walls can be left undecorated.
- ▶ Superior strength ensures a solid background for heavy duty fixings.

COMPLEMENTARY PRODUCTS

- ▶ Star Performer® Foundation
- ▶ Masterlite Pro Coursing Bricks
- ▶ Masterlite Pro
- ▶ Holcim Mortar
- ▶ Holcim Cement
- ▶ Holcim Concrete

APPLICATIONS

- ▶ Specifically manufactured for internal use in retail and commercial buildings.
- ▶ Can be used above and below the damp proof course for internal walls.
- ▶ Suitable for use in corridors and partition walls.
- ▶ 100mm can be used for the inner leaves of external cavity walls.
- ▶ Available in solid format for both 100mm and 140mm width in 10.4 N/mm² strength, suitable for the inner leaves of partition walls and corridors.

Environmental Product Declarations are available. Speak to your sales representative or call our technical department for details.



TECHNICAL DATA

Block Type		Solid	Solid
Face Size (mm)		440x215	440x215
Thickness (mm)		100	140
Dimensional Tolerances		D1	D1
Mean Unit Strength (N/mm ²)		10.4	10.4
Net Dry Density (kg/m ³)		1450	1450
Thermal Conductivity (W/mK) Based on tabulated values from BS EN 1745	Internal	0.57	0.57
	External	0.61	0.61
Thermal Resistance (m ² K/W)	3% Moisture	0.175	0.246
	5% Moisture	0.164	0.230
Sound Insulation (Rw dB) Based upon mass law calculation, assuming plaster both sides		39	41
Fire Resistance (hrs) Based on data from NA to EC6 Part 1-2, single leaf walls with no finishes. Assumed <1.0 of the permitted load capacity is being used	Load-bearing	2	3
	Non load-bearing	4	>4
Reaction to Fire Classification to EN 13501-1		Class A1	Class A1
Moisture Movement (mm/m)		<0.8	<0.8
Water Vapour Diffusion Coefficient μ Based on tabulated values from BS EN 1745		5/15	5/15
Durability Based on tabulated values in accordance with table 15, PD 6697:2010		Frost Resistant	Frost Resistant
Bond Strengths (N/mm ²) Based on tabulated values from BS EN 998-2 Annex C		0.15	0.15
Mortar Designation	Class iii for walls above DPC	1:1:6 Cement:Lime:Sand 1:5 to 6 Cement:Sand	1:1:6 Cement:Lime:Sand 1:5 to 6 Cement:Sand
	Class ii for walls below DPC	1:1/2:4 Cement:Lime:Sand 1:3 to 4 Cement:Sand	1:1/2:4 Cement:Lime:Sand 1:3 to 4 Cement:Sand

Product Data	Solid 10.4 N	Solid 10.4 N
Thickness	100	140
Unit Weight (kg) Based upon 3% moisture content by weight	14.13	19.78
Laid Weight (kg/m ²)	151	212
Pack Size (m ²)	9.0	6.0
Full Load Qty (m ²)	171	114
Available Finishes	Fairfaced	Fairfaced

GENERIC GREEN GUIDE RATING

Outer Leaf	Inner Leaf	Partition	No Finish
Brick	Masterlite Pro Fairfaced	-	A+
Render on Masterdenz	Masterlite Pro Fairfaced	-	A+
Render on Masterlite Pro	Masterlite Pro Fairfaced	-	A+
-	-	Masterlite Pro Fairfaced	A

Ratings based upon generic Green Guide values supplied by BRE Global Ltd. <https://bregroup.com/products/green-guide>.

SUSTAINABILITY & LOCAL SOURCING

Energy use and greenhouse gas emissions

Holcim UK is at the forefront of sustainability and has committed to reducing both energy and greenhouse gas intensity 5% year-on-year.

Recyclable

100% of the product can be recycled thus reducing the amount of material that is sent to landfill.

Manufacturing location

Produced in the UK, with locally sourced materials under strict environmental and social legislation, for local supply.

Circular economy

We will maximise reuse and recycle, with zero waste to landfill. We improve resource efficiency through reuse, recovery and/or recycling of waste materials in our production processes. Plus, we minimise the generation of both hazardous and non-hazardous waste.

Responsible sourcing

Holcim UK was the first UK construction company to achieve accreditation to the BES 6001 Framework Standard for the Responsible Sourcing of Construction Products.

Holcim UK has achieved a 'Very Good' rating for major product groups. The BES 6001 standard assesses:

- ▶ Quality Management
- ▶ Environmental Management
- ▶ Health and Safety Management
- ▶ Greenhouse Gas Emissions
- ▶ Minimising Raw Material Usage
- ▶ Labour Practice
- ▶ Biodiversity
- ▶ Community Engagement.

POLICIES

Holcim UK policies on the environment and community, health and safety and sustainable solutions for different product applications can be viewed on our website www.holcim.co.uk.

COSHH DATA

Full COSHH data on the Holcim range of products is available on request. Please email building.products@holcim.co.uk.

MANUFACTURING STANDARD

The Masterlite Pro Fairfaced range is manufactured using a semi-dry process and is compliant to European Standard BS EN 771-3 and complies with Assessment and Verification of Constancy of Performance (AVCP) system 4, Category II masonry units. All Holcim products are manufactured in accordance with ISO 9001 with factory compliance to ISO 14001.

TECHNICAL SUPPORT

For technical support, including assistance with the preparation of specifications, speak with your sales representative or contact our technical services team via: building.products@holcim.co.uk or call **01285 646900**.

The information contained within this publication was accurate at time of production. However, Holcim UK reserves the right to introduce modifications or changes to detail at any time without notice. No charge is levied for this publication or advice therein, and accordingly the company, its employees and authorised agents can accept no liability whatsoever, either indirectly or directly arising from the use of its products.